

Considerations on the significance of the pre-hydration state for the long-term safety functions of bentonite –

Implementer's Perspective

Paul Marschall, Olivier Leupin, Florian Kober, Benoit Garitte
(all Nagra)

With contributions from:


- Prof. Laloui / Prof. Ferrari and co-workers (EPFL)
- Prof. Romero and co-workers (UPC)
- Drs. Keller and Holzer (ZHAW)

BEACON Workshop
Mechanical properties of bentonite barriers
Kaunas, June 19-20, 2017



Outline – Considerations on the role of the pre-hydration state ...


- ... with respect to the long-term safety functions of bentonite



1 Spectrum of Applications – Bentonite-based material


■ Bentonite-based Sealing Material in Radioactive Waste Disposal – Applications

- HLW near-field
- Tunnel seals & shaft seals
- Borehole (bh) sealing
 - surface bh
 - underground bh (*horizontal, inclined*)



1 Spectrum of Applications – Bentonite-based material

- **HLW Near-field** – Issues related to the **As-Built State** (pre-hydration)




Emplacement tests: significant segregation

Construction gaps

Construction gaps


1 Spectrum of Applications – Bentonite-based material

- **Tunnel seals / shafts** – Wide range of designs (role of pre-hydration state?)



1 Spectrum of Applications – Bentonite-based material

■ Borehole sealing and special applications





1 Spectrum of Applications – Bentonite-based material

- It's all applications in common:
 - How can sensible technical requirements and QA/QC procedures be formulated for emplacement?
 - How can long-term performance be demonstrated?

2 Performance Assessment – A General Workflow

■ Generic PA-Workflow – Criteria based indicator approach



Safety functions

- mechanical confinement of canister
- retention of RN in the near-field
- attenuated release of RN
- ...

Processes, detrimental effects

- Repository induced effects (THMC)
- Effects rel. to long-term evolution
- ...

Functional indicators

- canister displacement
- swelling pressure P_s
- bentonite dry density ρ_d
- bentonite temperature T_{bent}
- ...


Performance measures

(compliance in entire assessment period)

- bentonite thickn. $M_{bent,min} < xy \text{ cm}$
- $P_{s,min} > xy \text{ MPa}$
- $\rho_{d,min} > xy \text{ Mg/m}^3$
- ...

2 Performance Assessment – A General Workflow

- **Generic PA-Workflow** – Where do we need help from RD&D (BEACON!)?



Nagra NTB 14-13

Processes, detrimental effects

- completeness of FEP list
- relevance for given repos. concept
- ...

Concepts, Modelling tools

- reliable concept. frameworks (THM)
- verified codes & validated models
- robust appraisals for parameter estimation (multi-scale approaches)
- ...

Model-based system analyses

- Powerful THM-C modelling tools
- Tools for probabilistic assessments
- ...

Repository Optimisation and QA/QC

- Novel emplacement techniques
- Guidance for balanced QA/QC
- ...

3 The Role of the As-Compacted State – Considerations

■ Microstructure of bentonite – Well-established conceptual frameworks describing natural state

- microfabric of solid components:
(classified in hierarchical order)

→ Clay platelets

→ Stacks (... made-up of platelets)

→ Aggregates (... made-up of stacks)


→ Assemblage / cluster (...)

- hierarchy of pore space (defined by the state of pore water):

→ micropores (interlayer pw)


→ mesopores (weakly bound pw)

→ Macropores (free pw)




Clay structures after Craig (2004)

Bradbury&Baeyens (2003)



Kaufold (2009)





3 The Role of the As-Compacted State – Considerations

- **Well-established conceptual framework** – Confirmation by mercury intrusion porosimetry (MIP)



Microstructure at the **as-compacted state**

✓ **SEM**, $e = 0.53$, $\rho_d = 1.80 \text{ Mg/m}^3$, $w = 5\%$


✓ **MIP**, double porosity structure



✓ **SEM of Single Grain**, $e = 0.53$, $w = 5\%$



MX-80
granular bentonite
(Apparent grain size
Distribution)



$\rho_d = 2.10 \text{ Mg/m}^3$


$\rho_d = 1.80 \text{ Mg/m}^3$

$\rho_d = 1.5 \text{ Mg/m}^3$

Seiphoori (2014)
Ferrari et al. (2015)

3 The Role of the As-Compacted State – Considerations

- **Hydration of the compacted material** – Evidence from mercury intrusion porosimetry (MIP)



Romero &
co-workers



3 The Role of the As-Compacted State – Considerations

■ Hydration of the compacted material – Independent evidence from 3-D imaging with cryo-FIB-nt



- low and high density samples (0.39 Mg/m^3 , 1.58 Mg/m^3) imaged with a resolution of around 10 nm

- both samples fully saturated

- only 1 % macroporosity detected in the high density sample!





Sample name	wt.% of water	vol.% of water	Saturation	Dry density [kg/m^3]
Ben I	68.8	85.6	100%	0.39
Ben IV	21.5	42.4	96%	1.58



3 The Role of the As-Compacted State – Considerations

■ Hydration of the compacted material – Suction measurements






Oral presentation
by Aldo Madatschi

Seiphoori (2014)

3 The Role of the As-Compacted State – Considerations

- Hydration of the compacted material – Air injection test under oedometric conditions



Romero et al. (2017)

3 The Role of the As-Compacted State – Considerations


- **Some preliminary interpretations & conclusions**

- the evolution of micro-fabric during the hydration process is the driver for the homogenisation process
- in the density range between 1.5 and 1.6 Mg/m³ the bi-modal structure goes lost after hydration
- the effect of the initial (as-compacted) density variation on the homogenisation of the hydrated material is yet to be investigated




4 A glance on the workshop programme – Highlights

■ Evidence from Large Scale In-situ Experiments (I)

- EB Experiment (Mont Terri)
 - artificial hydration started in 2002
 - dismantling in 2013
 - full saturation confirmed by comprehensive sampling
 - significant variability in dry density after dismantling
 - enhanced densities measured above the canister



Plenary presentation
by Juan Carlos Mayor






A glance on the workshop programme – Highlights

■ Evidence from Large Scale In-situ Experiments (II)

- FEBEX-DP Experiment (Grimsel Test Site)

- heating & hydration started in 1997
- final shut-off and dismantling in 2015
- full saturation reached in cold sections
- incomplete saturation around canisters
- construction joints closed, but visible!
- moderate variability of densities in cold cross-sections
- significant variability of densities in hot cross-sections

Plenary presentation
by Maria Victoria Villar





4 A glance on the workshop programme – Highlights

■ Experimental evidence (laboratory scale)

- Buffer homogenisation - Large scale test (SH1/SH2) by Clay-Tech (SKB's EBS-Task Force)

- comprehensive test programme (small/large scale)
- SH2: dismantling after 1.5 y; SH1 ongoing
- outstanding data set for model development (radial, axial swelling, ...)
- significant variability in swelling pressure after 2.5 y of hydration

Plenary presentation by Ann Dueck



5 Messages and Remarks – Implementer's perspective

- The **as-built / pre-hydration state** forms the **initial conditions** for the **assessment of long-term performance** of the (bentonite based) Engineered Barrier System
- Advise is sought from the BEACON research team concerning:
 - the drivers of the homogenisation process during hydration and the detrimental effect that could hinder the compliance with the specified performance measures
 - reliable prediction of homogenisation for the full range of considered detrimental effects (incl. heat, temperature, gas)
 - optimised emplacement procedures

**thank you
for your attention**

nagra.